

AME 6095



Vacuum Casting (VC)
Material Datasheet



UV-stable, water clear vacuum casting material. Has excellent mechanical properties and can simulate thermoplastics.

Measurement	Value
Shore Hardness	82D
Tensile Strength	60 MPa
Young's Modulus in Flexure	2,000 MPa
Impact Strength	10 kJ/m2
Shrinkage	0.3%
Deflection Temp. Under Load	80°C
Elongation Break	30%

Actual values may vary depending on build conditions. Our technical team can advise.