

Image TBC

C-UV 9400



Stereolithography (SLA)
Material Datasheet



ABS-like white SL resin offering high accuracy and durability. Suitable for master patterns, concept models, and functional prototypes.

Measurement	Value
Shore Hardness	83D
Tensile Modulus	2,189 - 2,395 MPa
Flexural Strength	69 - 74 MPa
Flexural Modulus	2,692 - 2,775 MPa
Heat Deflection Temp.	58 - 70° C
Elongation Break	27 - 31%

Actual values may vary depending on build conditions. Our technical team can advise.